

FREE MAINTENANCE BATTERY

| Flooded battery | | | | | | | | | | |
|-----------------|---------|----------|---------------|---------------|--------|---------------|---------|--------------|----------|------------|
| Code | Voltage | Capacity | Cold Cranking | Res.Cap. | Tester | Terminal | Lid | Bottom | Layout | Per pallet |
| B213C | V | Ah 20h | A (EN) | minutes | | conical | X box C | Bottom Holds | positive | 6x3 |
| | 12 | 220 | 1400 | 510 at 25A | 1400 | 1 standard | C | B0 | Left | |

TOP ENERGY TIR




BOX AND LID COLOUR
Black


Technical Characteristics




BOX AND LID
PP



TEMPERATURE
All values are referred to 25°C



SULFORIC ACID
Density
1,28 +/- 0,01 g/ml
Approximate volume 14,7l



PLATES
Casted grids Pb/Sb alloy.



WEIGHT
58,5 ±5% Kg